



BICROELAST HPP / HMP

-10°C



Designed for installation as the bottom layer in two layer roofing system on buildings and constructions, for waterproofing of engineering structures and for vapour barrier. Can be used on new construction or repair on the rigid foundation. Not recommended to use as single ply waterproofing.



Torch-on application on to the prepared surface.

TECHNICAL DATA

PRODUCT	FLOW RESISTANCE, °C	MAXIMUM TENSILE FORCE L/T, N/50 mm	RESISTANCE TO TEARING, N	ELONGATION, %	REINFORCEMENT TYPE / WEIGHT
BICROELAST HPP	≥85	400±100 250±100	50±10 50±10	2.2±0.22 2.2±0.22	glass-fiber, 55 g/m ²
BICROELAST HMP	≥85	400±100 250±100	50±10 50±10	2.2±0.22 2.2±0.22	glass-fiber, 55 g/m ²

LOGISTIC DATA

PRODUCT	WEIGHT, kg/m ²	THICKNESS, mm	LENGTH, m	WIDTH, m	ROLLS PER PALLET
BICROELAST HPP	3.0-0.15	2.5±0.1	15 / 16	1	23
BICROELAST HMP	3.0-0.15	2.5±0.1	15 / 16	1	23