



BIPOL HPP

-15°C



Designed for installation as the bottom layer in two layer roofing system on buildings and constructions, for waterproofing of engineering structures and for vapour barrier. Can be used on new construction or repair on the rigid construction. Not recommended to use as single ply waterproofing.



Torch-on application to the prepared surface.

TECHNICAL DATA

PRODUCT	FLOW RESISTANCE, °C	MAXIMUM TENSILE FORCE L/T, N/50 mm	RESISTANCE TO TEARING, N	ELONGATION, %	REINFORCEMENT TYPE / WEIGHT
BIPOL HPP	≥85	400±100 250±100	50±10 50±10	2.2±0.22 2.2±0.22	glass-fiber, 55 g/m ²
BIPOL STANDART HPP	≥85	400±100 250±100	50±10 50±10	2.2±0.22 2.2±0.22	glass-fiber, 55 g/m ²

LOGISTIC DATA

PRODUCT	WEIGHT, kg/m ²	THICKNESS, mm	LENGTH, m	WIDTH, m	ROLLS PER PALLET
BIPOL HPP	3.0-0.150	2.5 ±0.1	15	1	23
BIPOL STANDART HPP	3.5-0.175	2.9 ±0.1	15	1	23