



BICROELAST EPP

-10°C



Designed for installation as the bottom layer in two layer roofing system on buildings and constructions, for waterproofing of engineering structures. Can be used on new construction or repair. Two layers of membrane can be used for the waterproofing of foundations (according to EN 13969). Not recommended to use as single ply waterproofing.



Torch-on application to the prepared surface.

TECHNICAL DATA

PRODUCT	FLOW RESISTANCE, °C	MAXIMUM TENSILE FORCE L/T, N/50 mm	RESISTANCE TO TEARING, N	ELONGATION, %	REINFORCEMENT TYPE / WEIGHT
BICROELAST EPP 2.5 kg	≥85	600±100 500±100	180±50 180±50	50±25 50±25	polyester, 160 g/m ²
BICROELAST EPP	≥85	600±100 500±100	180±50 180±50	50±25 50±25	polyester, 160 g/m ²
BICROELAST EPP 4.0	≥85	600±100 500±100	180±50 180±50	50±25 50±25	polyester, 160 g/m ²

LOGISTIC DATA

PRODUCT	WEIGHT, kg/m ²	THICKNESS, mm	LENGTH, m	WIDTH, m	ROLLS PER PALLET
BICROELAST EPP 2.5 kg	2.5±0.10	-	16	1	23
BICROELAST EPP	3.0-0.15	2.5±0.1	15	1	23
BICROELAST EPP 4.0	4.0-0.20	3.2±0.1	16	1	23