



MIDA STANDARD PV S

-10°C



Designed for installation as the bottom layer in two layer roofing system on buildings and constructions, for waterproofing of engineering structures and for vapour barrier. Can be used on new construction or repair. Not recommended to use as single ply waterproofing.



Torch-on application to the prepared surface. Material can also be mechanically fixed and the membrane overlapping joints - torch welded.

TECHNICAL DATA

PRODUCT	FLOW RESISTANCE, °C	MAXIMUM TENSILE FORCE L/T, N/50 mm	RESISTANCE TO TEARING, N	ELONGATION, %	REINFORCEMENT TYPE / WEIGHT
MIDA STANDARD PV S4	≥85	600±200 500±200	200±100 200±100	50±20 50±20	polyester
MIDA STANDARD PV S4.5	≥85	600±200 500±200	200±100 200±100	50±20 50±20	polyester

LOGISTIC DATA

PRODUCT	WEIGHT, kg/m ²	THICKNESS, mm	LENGTH, m	WIDTH, m	ROLLS PER PALLET
MIDA STANDARD PV S4	-	4.0±0.2	10	1	23
MIDA STANDARD PV S4.5	-	4.5±0.1	10	1	23