



BICROST HMM YAM 2000

0°C



Designed for installation as the bottom layer in two layer roofing system on buildings and constructions, for waterproofing of engineering structures and for vapour barrier. Can be used as underlay for bitumen shingles or other types of roofing for pitched roofs. Not recommended to use as single layer waterproofing.



Glued to the prepared surface with cold- or hot-applied bitumen mastic. When used as underlay can be fastened mechanically.

TECHNICAL DATA

PRODUCT	FLOW RESISTANCE, °C	MAXIMUM TENSILE FORCE L/T, N/50 mm	RESISTANCE TO TEARING, N	ELONGATION, %	REINFORCEMENT TYPE / WEIGHT
BICROST HMM YAM 2000	≥80	400±150 300±150	30±10 30±10	2.2±0.22 2.2±0.22	glass-fiber, 55 g/m ²

LOGISTIC DATA

PRODUCT	WEIGHT, kg/m ²	THICKNESS, mm	LENGTH, m	WIDTH, m	ROLLS PER PALLET
BICROST HMM YAM 2000	2.0±0.25	-	15	1	30