

BIPOL STANDART HKP

Glass fibre based SBS Modified Torch-On Cap Sheet



Introduction

BIPOL STANDART HKP mineral membranes are economical, high performance glass fibre based waterproofing materials designed to suit requirements of both new build and remedial roofing applications.




Product Description

BIPOL STANDART HKP is a fibreglass based, slate covered Torch – On Cap sheet, saturated and coated with high quality SBS (Styrene-Butadiene-Styrene) modified bitumen. The membrane carrier is a tough glass fibre reinforcement, giving the material excellent dimensional stability and very high mechanical strength. The upper layer is coated with slate protecting material from ultraviolet exposure and lower layer is finished with thermofusible film for fast and consistent Torch – On application.

BIPOL STANDART HKP are reliable, environmentally friendly materials with excellent performance and economy characteristics. These products can be applied to all suitable Torch – On or Pour and Roll underlays as top layer in built up waterproofing systems. Not recommended for use as single ply waterproofing.

Product Features

- Excellent low temperature flexibility at -15°C
- Guided (snowflake print) rapid melt film for accurate and consistent Torch -On application
- High resistance to foot marking
- High puncture resistance
- High quality glass fibre carrier
- SBS modified bitumen binder formulated to ensure high performance
- 10 year material guarantee within approved waterproofing system
- Range of 5 mineral colours



Application

BIPOL STANDART HKP materials can be used as cap sheet in built up waterproofing systems on new built or refurbished flat roofs as well as part of overlay systems to existing asphalt waterproofing.

BIPOL STANDART HKP should be installed in accordance with BS 8217: 2005 Code of Practice for Reinforced bitumen membranes for roofing, constantly observing TechnoNICOL installation recommendations and guidance. BIPOL STANDART HKP membranes are applied by traditional Torch – On methods onto previously installed base layer/underlay, clear of any debris or sharp projections, primers shall be used to prepare substrate for achieving most effective waterproofing longevity.

The membranes should be heated carefully ensuring the complete melt of dispersible film as work proceeds and maintaining 5 mm bead extrusion from all laps. Side laps must follow the manufactured mineral free pilot selvedge with end laps at minimum of 100 mm. The cap sheet should be offset 300 mm from the underlay to avoid side build up.

Nr. 18

TECHNICAL DATA SHEET 06.2016

Harmonised standard

EN 13707:2004 + A2:2009

Health and Safety

Health and Safety should be observed at all times in accordance with HSE and Industry guidance. Specific Risk Assessments and Method Statements should be produced by contractors where necessary to ensure Working at Heights, Fire Safety and Manual Handling rules are compliant with current law and regulations. Health and safety data sheets are available for all materials on request from TechnoNICOL Technical Service Department.

Availability

Product Name	Product Code	Roll Dimensions (m)	Weight (kg/m ²)
BIPOL STANDART HKP	47994	8/10 x 1	4.5 ± 0.225

Performance and Key Properties

Properties	Test Method	Declared Performance
Reinforcement type and weight		Glass fibre, 55 g/m ²
Maximum tensile force L/T, N/50mm	EN 12311-1	400/250±100
Elongation, %	EN 12311-1	2.2/2.2±0.22
Resistance to tearing (nail shank), N	EN 12310-1	50/50±10
Flow resistance at elevated temp. °C	EN 1110	≥ 85
Flexibility at low temp. °C	EN 1109	≤ -15
Watertightness, kPa	EN 1928	100
Water vapour transmission properties	EN 1931	μ=20 000
External fire performance	EN 13501-5 ENV 1187:2002, test 2*	Broof (t2)*

*This material is part of a two-layer roofing system and corresponds to the Broof only in combination with a second layer of roofing system.

Quality Assurance

BIPOL STANDART HKP materials are manufactured following ISO 9001: 2008 Quality Management System and Environmental Management System approved to ISO 14001: 2004.

Technical Service and Other Products

Specialist advice and information on other compatible products is available on www.tn-europe.com