ONE VERTICAL

Item Code: SEE DN Issue date: 20.09.20th

Review # 02

Page 1 of 3

DESCRIPTION OF THE PRODUCT

One-component, coloured, liquid applied, UV-resistant waterproofing membrane, specifically formulated for vertical applications even under extreme conditions: low and high temperatures (from 0°C to +45°C), damp or very wet substrates. The product remains stable to thermal shocks.

USE FIELD

Vertical walls: plaster, concrete, brick, fibre cement, metal and ceramic coatings even those with permanent problems of excess damp. The product becomes rainproofed, although not fully cured, according to the Rain-Proof Time Table provided.

Rain-Proof Time Table

Temperature of application	Rain-proofed in:
20°C	2 h
15°C	2 h 30 minutes
10°C	3 h
5°C	4 h
0°C	5 h

SURFACE PREPARATION

Thoroughly clean the substrate to be treated to remove: dust, crumbly parts, foreign or non-stick substances. Before applying **ONE VERTICAL**, restore any missing volumes (from 2 to 20 mm), with **PRE-ONE**, a quick-setting premixed product, also applicable at low temperatures (0°C). After applying **PRE-ONE**, wait at least 12 hours before overapplying **ONE VERTICAL**. Follow the instructions contained in the most recent product's TDS.

APPLICATION

Before applying, quickly mix the product. **ONE VERTICAL** is ready to use and does not require a primer nor protective topcoat. Apply **ONE VERTICAL** with a short-haired roller, flat brush, metal spatula (on smooth surfaces) and airless spray gun **(LARIUS series ZEUS, DRAGON or THOR)**. For further specifications, contact WINKLER technical office. Apply the product in a single coat, covering the substrate completely with no gaps.

WARNING

The product is ready to use so, <u>DO NOT</u> dilute it with water nor solvents.

TOOL MAINTENANCE

Clean tools with denatured ethyl alcohol if the product is still wet. Mechanically remove the product if already dry.

Winkler Srl







SURFACE CLEANING

If, with aging and use, a cleaning of the surface of **ONE VERTICAL** is needed, use a solution of water and denatured alcohol in a 1:1 ratio.

CONSUMPTION

 $350 - 400 \text{ g/m}^2$ in single coat.

PACKAGING

5 - 20 Kg buckets

COLORS

White, light grey, grey, red, terracotta, green.

STORAGE

The product in its original and unopened packaging and stored in a dry and protected place has a stability of 12 months. Store at temperatures between + 5 ° C and + 35 ° C.

SAFETY INSTRUCTIONS

PRECAUTIONS

For information about safety, user must refer to the most recent Safety Data Sheet, edited in accordance with the regulations in force, which contains physical, toxic and other data about the product in use.

ECOLOGY

Do not dispose the product and/or empty containers in the environment. Consult the most recent Safety Data Sheet for further information about disposals.

TECHNICAL FEATURES OF WET PRODUC	T
----------------------------------	---

Appearance	Liquid paste
Colour	White, light grey, grey, red, terracotta,
	green
Specific weight at 20°C (g/cm³)	1.40 ± 0.05
Dry content (%)	98 ± 1
Brookfield viscosity at 20°C (Cps)	22,500 ± 500

PERFORMANCE OF THE PRODUCT IN OPERATION

Operating temperature	-50°C + 80°C
Weathering resistance	Excellent
Resistance to U.V. rays	Excellent
Low temperature flexibility (-26°C) (ASTM D522)	No break
Low temperature flexibility (-26°C) after 1000 hrs of Accelerated weathering (ASTM D522)	No break

TECHNICAL SHEET

Winkler Srl

Via M. Buonarroti, 15 - 20093 Cologno Monzese (Mi) - Italy | Tel. +39 02 26 700 605 - Fax +39 02 26 700 621 info@winklerchimica.com - www.winklerchimica.com



Tensile strength (ASTM D 2370)	1,100 PSI – 7.5 N/mm ²
Elongation at breaking point (ASTM D 2370)	60%
Elongation at breaking point after 1000 hrs of Accelerated weathering	47%
Resistance to negative counter-pressure	4 bar
Resistance to positive pressure	6 bar
Water absorption after 24 h (%) (ASTM D471)	<0.1
Water absorption after 7 days (%)(ASTM D471)	<0.5
Permeability class	SD 1 (>0.5 <1)
Application temperatures	From 0°C to +45°C

Adhesion to support (UNI EN 1542)

Adhesion to support (N/mm²) after 14 days	
	≥ 2.60
TILE ²	≥ 1.25
Adhesion to support (N/mm²) after 14 days of water immersion	
	≥ 2.00
TILE ²	≥ 1.10
Adhesion to support (N/mm ²) after 14 days of salted water immersion	
	≥ 2.00
TILE ²	≥ 1.2 0

Adhesion to support (N/mm ²) after 14 days of pH2 water immersion	
	≥ 1.80
TILE ²	≥ 1.25

Adhesion to Metal (N/mm²)	≥2
---------------------------	----

<u>Notes:</u>

¹ Concrete delamination

² Tile break

PRODUCT FOR PROFESSIONAL ONLY

Product meets with prescriptions of 2003/53/CE Directive.

The information contained in this technical data sheet is to the best of our knowledge correct. However, by no means can it be considered a guarantee, as usage, working area and application of the product in accordance with the instructions given and their success in application is beyond our control and is dependent on a number of factors. We decline any responsibility for the improper use of the product as the application recommendations contained herein are to be considered as a general guideline if at all in doubt, preliminary tests should be carried out. WIKLER Sr.I. reserves the right to modify and update said data sheets without prior notice. Clients are kindly requested to verify that they are in possession of the current edition.

Winkler Srl

