


ECOFLEKS V / PV 4.5 kg MINERAL

0°C



Designed for installation as the top layer in two layer roofing system on buildings and constructions. Can be used on new construction or repair. Suitable for local repair. Not recommended to use as single ply waterproofing.



CLASS E

Torch-on application to the prepared surface.

TECHNICAL DATA

PRODUCT	FLOW RESISTANCE, °C	MAXIMUM TENSILE FORCE L/T, N/50 mm	RESISTANCE TO TEARING, N	ELONGATION, %	REINFORCEMENT TYPE / WEIGHT
ECOFLEKS V 4.5 kg MINERAL	≥100	400±150 300±150	50±10 50±10	4.0±2.0 4.0±2.0	glass-fiber, 55 g/m ²
ECOFLEKS PV 4.5 kg MINERAL	≥100	600±150 450±150	180±50 180±50	35±10 35±10	polyester, 140 g/m ²

LOGISTIC DATA

PRODUCT	WEIGHT, kg/m ²	THICKNESS, mm	LENGTH, m	WIDTH, m	ROLLS PER PALLET
ECOFLEKS V 4.5 kg MINERAL	4.5±0.2	-	8/10	1	23
ECOFLEKS PV 4.5 kg MINERAL	4.5±0.2	-	8/10	1	23

AVAILABLE COLOURS

