

ECOFLEKS V Mineral

Glass fibre based APP Modified Torch-On Cap Sheet



Introduction

ECOFLEKS V mineral membranes are economical, high performance glass fibre based waterproofing materials designed to suit requirements of both new build and remedial roofing applications.




Product Description

ECOFLEKS V is a glass fibre based, slate covered Torch – On Cap sheet, saturated and coated with bitumen containing APP (Atactic Polypropylene) polymer modifier. The membrane carrier is a tough glass fibre reinforcement, giving the material excellent dimensional stability and very high mechanical strength. The upper layer is coated with slate protecting material from ultraviolet exposure and lower layer is finished with thermofusible film for fast and consistent Torch – On application.

ECOFLEKS V are reliable, environmentally friendly materials with excellent performance and economy characteristics. These products can be applied to all suitable Torch – On underlays as top layer in built up waterproofing systems. Not recommended for use as single ply waterproofing.

Product Features

- Excellent flow resistance at elevated temperature 100°C
- Guided (snowflake print) rapid melt film for accurate and consistent Torch -On application
- High resistance to foot marking
- High puncture resistance
- APP polymer modified bitumen formulated to ensure high performance
- Range of 5 mineral colours



Application

ECOFLEKS V materials can be used as cap sheet in built up waterproofing systems on new built or refurbished flat roofs as well as part of overlay systems to existing asphalt waterproofing.

ECOFLEKS V membranes should be installed in accordance with BS 8217: 2005 Code of Practice for Reinforced bitumen membranes for roofing, constantly observing TechnoNICOL installation recommendations and guidance. ECOFLEKS V membranes are applied by traditional Torch – On methods onto previously installed base layer/underlay, clear of any debris or sharp projections, primers shall be used to prepare substrate for achieving most effective waterproofing longevity.

The membranes should be heated carefully ensuring the complete melt of dispersible film as work proceeds and maintaining 5 mm bead extrusion from all laps. Side laps must follow the manufactured mineral free pilot selvedge with end laps at minimum of 100 mm. The cap sheet should be offset 300 mm from the underlay to avoid side build up of overlaps.

Nr. 28

TECHNICAL DATA SHEET 06.2016

Harmonised standard

EN 13707:2004 + A2:2009

Health and Safety

Health and Safety should be observed at all times in accordance with HSE and Industry guidance. Specific Risk Assessments and Method Statements should be produced by contractors where necessary to ensure Working at Heights, Fire Safety and Manual Handling rules are compliant with current law and regulations. Health and safety data sheets are available for all materials on request from TechnoNICOL Technical Service Department.

Availability

Product Name	Product Code	Roll Dimensions (m)	Weight (kg/m ²)
ECOFLEKS V 4.5 Kg Mineral	386968	8/10 x 1	4.5 ± 0.20

Performance and Key Properties

Properties	Test Method	Declared Performance
Reinforcement type and weight		Glass fibre, 55 g/m ²
Maximum tensile force L/T, N/50mm	EN 12311-1	400/300±150
Elongation, %	EN 12311-1	4/4±2
Resistance to tearing (nail shank), N	EN 12310-1	50/50±10
Flow resistance at elevated temp. °C	EN 1110	≥ 100
Flexibility at low temp. °C	EN 1109	≤ 0
Watertightness, kPa	EN 1928	100
Water vapour transmission properties	EN 1931	μ=20 000
Reaction to fire	EN 13501-1:2004	Class E

Quality Assurance

ECOFLEKS V materials are manufactured following ISO 9001: 2008 Quality Management System and Environmental Management System approved to ISO 14001: 2004.

Technical Service and Other Products

Specialist advice and information on other compatible products is available on www.tn-europe.com